


Vivid Shade



Technical Data

Composition	30% polyester / 70% PVC
Width	2,000mm & 3,000mm
Weight	425gsm +/-5%
Thickness	0.63mm +/-5%
Opacity/Openness	≥ 5%
Light Fastness	≥ 5 (Blue wool scale)
Coating	Polyester yarns with PVC coating
Flame Retardant	Tested to AS1530.3
Cleaning	Wipe clean with warm soapy water and damp cloth



Solar Properties

USA Standard Tested To Ashrae 74-73

	Ts	Rs	As	Tv/Vlt	O-F	Shading Coefficients (Sc)		
						3mm CL.	6mm CL.	9mm CL.
White	24	62	14	20	7	0.28	0.38	0.25
White/Lily	21	57	22	16	6	0.26	0.41	0.26
White/Stone	22	59	19	18	7	0.27	0.40	0.26
White/Bone	22	54	24	17	7	0.27	0.43	0.26
Silver/Linen	21	43	36	15	6	0.30	0.49	0.27
Linen/Bronze	15	30	55	11	6	0.28	0.56	0.28
Black/Sable	10	12	78	9	8	0.28	0.66	0.30
Black/Bronze	8	5	87	8	7	0.29	0.69	0.31
Bronze/Grey	10	13	77	8	6	0.28	0.65	0.30
White/Silver	15	49	36	11	5	0.24	0.45	0.27
White/Grey	14	37	49	11	7	0.25	0.52	0.28
Silver/Grey	12	23	65	8	6	0.27	0.59	0.29
Black/Beige	7	11	82	7	6	0.27	0.66	0.30
Charcoal/Grey	9	8	83	8	8	0.29	0.68	0.30
Charcoal	10	6	84	9	8	0.30	0.69	0.30
Black	7	4	89	7	7	0.28	0.70	0.31

Ts Solar Transmittance

As Solar Absorbance

Tv Visual Light Transmission

G-Value % Solar Radiation through Fabric

Rs Solar Reflection

Tuv Ultraviolet Transmittance

O-F Openness Factor

G-Total % Solar Radiation through Blind and Window

Melbourne Head Office

Building 1, Level 2, 630 Mitcham Road
Mitcham VIC 3132 Australia

P +61 3 9729 9970
E sales@texstyle.com.au

Learn more at
texstyle.com.au

