

Metroshade



Technical Data

Composition	100% polyester
Width	3,000mm
Weight	Blockout 400gs m +/-5% Light Filtering 260gsm +/-5%
Thickness	Blockout 0.55mm +/-5% Light Filtering 0.50mm +/-5%
Opacity/Openness	Blockout only tested to meet AS-2663-1999
Light fastness	≥ 6 (Blue wool scale)
Coating	Blockout coated with acrylic foam Light Filtering stiffened with acrylic
Flame Retardant	Product is designed and manufactured to comply with Building Code of Australia requirements for class 2 to 9 buildings.
Cleaning	Surface dust can be removed with vacuum or a soft cloth
Cutting Methods	Blockout - All cutting methods suitable Light Filtering - Ultrasonic cutting is recommended to avoid fraying edges

Solar Properties

	European standard tested to DIN EN 410: 2011						Tested to EN 14501	
	Ts	Rs	As	Tv/ Vlt	Tuv	O-F	Single Glass Reference Glazing A [g window 0.85] [U window 5.7] G-total	High Performance Glass Reference Glazing D [g window 0.32] [U window 1.1] G-total
Blockout	0	71	29	0	0	0	0.30	0.24
Dove/White LF	39	58	3	40	13	0.1	0.43	0.26
Ice Grey LF	38	59	3	39	12	0.4	0.42	0.26
Ecru LF	37	59	4	37	11	0.3	0.42	0.26
Moonstone LF	32	48	20	31	10	0.1	0.48	0.27
Nougat LF	32	49	19	31	10	0.2	0.47	0.27
Quill LF	31	46	23	29	10	0.3	0.49	0.27

Ts Solar Transmittance

As Solar Absorbance

Tv Visual Light Transmission

G-Value % Solar Radiation through Fabric

Rs Solar Reflection

Tuv Ultraviolet Transmittance

O-F Openness Factor

G-Total % Solar Radiation through Blind and Window

textstyle.com.au

Phone. 03 9729 9970



TEXTSTYLE